

# INDIAN Quality

## TECHNICAL SPECIFICATIONS

Composition		
Pile		80% PES 20% WO
Width	ISO3932	156 +1/-0 cm
Weight	EN 12127	1.020 grs/m2 ± 5%
Thickness	EN ISO 5084	4 mm ± 0,5 mm
Strength resistance	EN ISO 13934/1	
Warp		> 200 kg
Weft		> 300 kg
Abrasion resistance	EN ISO 12947	
Martindale		> 100.000 rubs
Colour Fastness		
Light	EN ISO 105-B02	≥ 6
Organic solvent cleaner	EN ISO 105-D02	≥ 4
Dry rubbing	EN ISO 105-X12	≥ 4-5
Wet rubbing	EN ISO 105-X12	≥ 4-5
Fire resistance	R. 118.02 (6,7 and 8 annexed)	E9*118R02/04*2039*01
Laceration resistance	EN 45545-2 annex A	80 N

## IS TREATMENTS

### IS-CLEAN

Water repellency: spray test ISO 4920 ≥ 4-5

### IS-ACTIVE

Water repellency: spray test ISO 4920 ≥ 4-5

Photocatalytic activity ASTM D 5075-96 OK

Photocatalytic abatement ISO 22197-1 > 22%

### IS-VITAL ACTIVE

Antibacterial protection ISO 20743 ≥ LOG.3

Water repellency: spray test ISO 4920 ≥ 4-5

Photocatalytic activity ASTM D 5075-96 OK

Photocatalytic abatement ISO 22197-1 > 22%

### IS-PURE

Antibacterial protection ISO 20743 ≥ LOG.3

### IS-NET

Antibacterial protection ISO 20743 ≥ LOG.3

Water repellency: spray test ISO 4920 ≥ 4-5

### IS-VIROPURE

Antibacterial protection ISO 20743 ≥ LOG.5

Antiviral protection ISO 18184 98% reduction in viral activity

### IS-VIRONET

Antibacterial protection ISO 20743 ≥ LOG.5

Antiviral protection ISO 18184 98% reduction in viral activity

Water repellency: spray test ISO 4920 ≥ 4-5

### IS-VIROACTIVE

Antibacterial protection ISO 20743 ≥ LOG.5

Antiviral protection ISO 18184 98% reduction in viral activity

Water repellency: spray test ISO 4920 ≥ 4-5

Photocatalytic activity ASTM D 5075-96 OK

Photocatalytic abatement ISO 22197-1 > 22%