

ATLANTIC Quality

TECHNICAL SPECIFICATIONS

Composition		
Pile		85% WO 15% PA
Width	ISO3932	156 +1/-0 cm
Weight	EN 12127	1.015 grs/m2 ± 5%
Thickness	EN ISO 5084	4 mm ± 0,5 mm
Strenght resistance	EN ISO 13934/1	
Warp		> 200 kg
Weft		> 300 kg
Abrasion resistance	EN ISO 12947	
Martindale		> 80.000 rubs
Colour Fastness		
Light	EN ISO 105-B02	≥ 6
Organic solvent cleaner	EN ISO 105-D02	≥ 4
Dry rubbing	EN ISO 105-X12	≥ 4-5
Wet rubbing	EN ISO 105-X12	≥ 4-5
Fire resistance	R. 118.02 (6,7 and 8 annexed) EN 45545-2 R21	E9*118R02/02*2051*00 HL3
Laceration resistance	EN 45545-2 annex A	≥ 80N

IS TREATMENTS

IS-CLEAN

Water repellency: spray test	ISO 4920	≥ 4-5
------------------------------	----------	-------

IS-ACTIVE

Water repellency: spray test	ISO 4920	≥ 4-5
Photocatalytic activity	ASTM D 5075-96	OK
Photocatalytic abatement	ISO 22197-1	> 22%

IS-VITAL ACTIVE

Antibacterial protection	ISO 20743	≥ LOG.3
Water repellency: spray test	ISO 4920	≥ 4-5
Photocatalytic activity	ASTM D 5075-96	OK
Photocatalytic abatement	ISO 22197-1	> 22%

IS-PURE

Antibacterial protection	ISO 20743	≥ LOG.3
--------------------------	-----------	---------

IS-NET

Antibacterial protection	ISO 20743	≥ LOG.3
Water repellency: spray test	ISO 4920	≥ 4-5

IS-VIROPURE

Antibacterial protection	ISO 20743	≥ LOG.4
Antiviral protection	ISO 18184	98% reduction in viral activity

IS-VIRONET

Antibacterial protection	ISO 20743	≥ LOG.4
Antiviral protection	ISO 18184	98% reduction in viral activity
Water repellency: spray test	ISO 4920	≥ 4-5

IS-VIROACTIVE

Antibacterial protection	ISO 20743	≥ LOG.4
Antiviral protection	ISO 18184	98% reduction in viral activity
Water repellency: spray test	ISO 4920	≥ 4-5
Photocatalytic activity	ASTM D 5075-96	OK
Photocatalytic abatement	ISO 22197-1	> 22%